

U.S. METALS Company

4819 Patata Street
 Cudahy, California 90201
 (213) 771-8312

CORE HOLE ANALYSIS August 7 1981

RED CLOUD
 COULTERVILLE, CA.
 TEST HOLE NO. 1

SAMPLE (depth-ft.)	SAMPLE WT. (grams)	FIRE ASSAY (03/ton)		FIRE ASSAY CHLORIDE BAKE (03/ton)		X-RAY (03/ton) Au
		Ag	Au	Ag	Au	
60-65	54.	00	00	1.3	0.1	0.57
65-70	MISSING	"	"	-	-	-
70-75	65.	"	"	1.6	TR	0.56
75-80	54.1	"	"	1.4	TR	0.51
80-85	39.4	"	"	1.4	0.1	0.48
85-90	69.6	"	"	2.1	0.1	0.48
90-95	MISSING	"	"	-	-	0.58
95-100	36.	"	"	1.7	TR	0.56
100-105	84.9	"	"	1.6	TR	0.62
105-110	39.1	"	"	TEST STOPPED		0.59
110-115	50.9	"	"	"	"	0.60
115-120	88.5	"	"	"	"	0.63
120-125	73.7	"	"	"	"	0.61
125-130	39.8	"	"	"	"	0.62
130-135	31.1	"	"	"	"	0.65
135-140	50.7	"	"	"	"	0.64
140-145	50.5	"	"	"	"	0.61
145-150	66.4	"	"	"	"	0.60

U.S. METALS Company

4819 Patata Street
Cudahy, California 90201
(213) 771-8312

CORE HOLE ANALYSIS
August 7 1981

RED CLOUD
COULTERVILLE, CA.
TEST HOLE NO. 2

SAMPLE (depth-ft.)	SAMPLE WT. (grams)	FIRE ASSAY (oz/ton)		FIRE ASSAY Chloride BAKE (oz/ton)		X-RAY (oz/ton) Au
		Ag	Au	Ag	Au	
65-70	60.6	0	0	1.5	TR	0.68
70-75	27.3	"	"	2.1	0.1	0.63
75-80	31.4	"	"	1.6	TR	0.67
80-85	73.4	"	"	1.7	0.1	0.67
85-90	56.2	"	"	2.0	0.1	0.64
90-95	125.8	"	"	2.3	TR	0.65
95-100	48.3	"	"	2.1	TR	0.50
100-105	67.6	"	"	2.2	0.1	0.69
105-110	42.0	"	"	2.5	0.2	0.72
110-115	42.2	"	"	2.1	0.1	0.73
115-120	60.4	"	"	3.0	0.1	0.72
120-125	48.5	"	"	3.1	0.2	0.65
125-130	52.	"	"	2.7	0.2	0.71
130-135	132.5	"	"	2.4	0.1	0.58
135-140	82.4	"	"	3.2	0.1	0.63
140-145	45.0	"	"	4.5	0.2	0.60
145-150	85.6	"	"	2.8	0.1	0.67
150-155	37.	"	"	3.1	0.1	0.62
155-160	28.8	"	"	3.7	0.2	0.62